

MORGAN'S PRIMER MINIO MARE A-07
MORGAN'S MARINE RED LEAD PRIMER
 Red lead based rust-inhibiting primer for ironwork



PROPERTIES

Anticorrosive primer with a blend of red lead and long-oil alkyd resin, high wetting power, suitable for protecting ironwork.

COATING SYSTEM

SURFACE PREPARATION

Iron:

remove any traces of rust and old flaking coats of enamel, dust, clean any dirt or grease stains with a cloth soaked in thinner. Allow to dry thoroughly, sand down and dust.

Apply one or two coats of MORGAN'S PRIMER MINIO MARE, leaving 24 hours between coats, allow to dry thoroughly for at least 24 hours.

Sand down and dust.

FINISH

Apply two coats of enamel, leaving at least 24 hours between coats.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application.

Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of MORGAN'S PRIMER MINIO MARE rust inhibitor, a blend of long-oil alkyd resin and red lead, in two coats to a thickness of 35 microns each, on suitably prepared metalwork.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

| | | | | | | | |
|---|--|----------------------------------|--|---|--|---|--|
| Theoretical spreading rate Per coat sq m/l 14 | | Thinner SYNTHETIC THINNER | | Equipment cleaning SYNTHETIC THINNER | | Roller application 30-40% SYNTHETIC THINNER | |
| Appearance and finish MAT | | Dust dry 2 HOURS | | Specific weight kg/l 1.63 | | Brush application 30-40% SYNTHETIC THINNER | |
| Colours ORANGE (for professional use only) | | Touch dry after 6-10 HOURS | | Solids by volume 48 | | Knife application = | |
| Exterior / interior use YES/YES | | Through drying after 24 HOURS | | Viscosity 180" FORD 4 | | Air assisted spraying 30-40% SYNTHETIC THINNER | |
| Shelf life 24 MONTHS | | Overcoating interval 24 HOURS | | Flash point 35°C | | NOZZLE DIAM. 1.7 - 2 PRESSURE 2 - 2.5 | |

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230

