

ANTIRUGGINE GLICEROFTALICA MORGAN'S PRIMER A-11
MORGAN'S PRIMER GLYCEROPHTHALIC RUST INHIBITOR



PROPERTIES

Rust-inhibiting primer for corrosion-inhibiting protection of ironwork, formulated with metal oxides and long-oil alkyd resin.

COATING SYSTEM

SURFACE PREPARATION

Iron: remove any traces of rust and old flaking coats of enamel, dust, clean any dirt or grease stains with a cloth soaked in thinner. Allow to dry thoroughly, sand down and dust.

Apply one or two coats of MORGAN'S PRIMER Glycerophthalic rust inhibitor, leaving 24 hours between coats; allow to dry thoroughly for at least 24 hours. Sand down and dust.

FINISH

Apply two coats of enamel, leaving at least 24 hours between coats.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of anticorrosive primer MORGAN'S PRIMER Glycerophthalic rust inhibitor, a blend of modified alkyd resin and metal oxides, on suitably prepared metalwork, in two coats to a thickness of 35 microns each.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 14		Thinner SYNTHETIC THINNER		Equipment cleaning SYNTHETIC THINNER		Roller application 10-15 % SYNTHETIC THINNER	
Appearance and finish MAT		Dust dry 2 HOURS		Specific weight kg/l 1.4 -1.6		Brush application 10-15% SYNTHETIC THINNER	
Colours GREY, ORANGE, RED (for professional use only)		Touch dry after 6-10 HOURS		Solids by volume 50		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 150''FORD 4		Air assisted spraying 10-15% SYNTHETIC THINNER	
Shelf life 24 MONTHS		Overcoating interval 24 HOURS		Flash point 35°C		NOZZLE DIAM. -1.7 - 2 PRESSURE -2 - 2.5	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230