

FONDO UNIVERSALE A RAPIDA ESSICCAZIONE
FAST DRYING UNIVERSAL PRIMER
 Rust-inhibiting primer for iron



PROPERTIES

Special base rust-inhibiting primer for surface preparation, particularly suitable as a primer when applying a finish with products containing aggressive solvents, nitro enamels etc.. Fast-drying product.

COATING SYSTEM

SURFACE PREPARATION

Iron: remove any traces of rust and old flaking coats of enamel, dust, clean any dirt or grease stains with a cloth soaked in thinner; allow to dry thoroughly, sand down and dust.

Apply two coats of FONDO UNIVERSALE A RAPIDA ESSICCAZIONE within 8 hours, or allowing at least 24 hours between coats, sand down and dust.

FINISH

After 24 hours, apply two coats of MORGAN'S FAST enamel.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of two coats of FONDO UNIVERSALE A RAPIDA ESSICCAZIONE to a thickness of 35 microns each on prepared metalwork.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 10		Thinner NITRO		Equipment cleaning NITRO		Roller application =	
Appearance and finish MAT		Dust dry 15'		Specific weight kg/l 1.3		Brush application =	
Colours WHITE		Touch dry after 30'		Solids by volume 45		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 180" FORD 4		Air assisted spraying 30-40 % NITRO THIN.	
Shelf life 24 MONTHS		Overcoating interval WITHIN 8 HOURS OR AFTER 24 HOURS		Flash point 23°C		=NOZZLE DIAM. 1.7mm PRESSURE 2.5 atm	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230

