

**MURALITE 2000**  
Plasticizer mat primer double covering for wood  
and masonry



## PROPERTIES

High-opacity mat plasticizing primer, for exterior and interior use.

Features outstanding filling and covering power, and dilatation.

Ideal as a base coat to preparing woodwork for painting with synthetic or synthetic-oil enamels.

Primer recommended for wood due to be enamelled and for walls due to be decorated.

Sandable 12 hours after application.

## COATING SYSTEM

### SURFACE PREPARATION

**New wood:** the substrate must be perfectly dry; maximum relative humidity 12%; sand and dust.

**Previously coated wood:** if the primer coating is sound, sand and dust; otherwise, strip completely using REMOVER.

**Standard plaster:** allow to dry out, clean dirt stains.

**Old walls:** remove old paintwork, clean dirt stains.

Fill with MORGAN'S STUCCO IN PASTA or IN POLVERE.

Apply two coats of MURALITE 2000, leaving at least 12 hours and sanding between coats.

### FINISH

After 24 hours, apply two coats of enamel, leaving at least 24 hours between coats.

## WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

### TENDER SPECIFICATION ITEM

Application of two or more coats of MURALITE 2000 to a thickness of 35 microns each on suitably prepared wooden substrates, sanding between coats.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 12		Thinner TURPENTINE		Equipment cleaning TURPENTINE		Roller application 5-10 % TURPENTINE	
Appearance and finish MAT		Dust dry 1 HOUR		Specific weight kg/l 1.56		Brush application 5-10% TURPENTINE	
Colours WHITE		Touch dry after 4 HOURS		Solids by volume =		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 20" FORD 8		Air assisted spraying 15-20% TURPENTINE	
Shelf life 36 MONTHS		Overcoating interval 12 HOURS		Flash point 35°C		=NOZZLE DIAM. 1.5-1.7 mm PRESSURE 2 atm	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

**J COLORS S.p.A.**

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230

