

MURALITE A-19

Mat primer covering for wood and masonry



PROPERTIES

White mat brush-on filler particularly suitable as a primer to prepare woodwork for enamelling and for producing prestigious wall finishes.

Features outstanding filling power, permeability and dilatation; easily sanded after 5 – 7 hours.

Resin-based and easily sanded, this mat primer covering with high extender content produces a film boasting considerable filling power.

COATING SYSTEM

SURFACE PREPARATION

New wood: the substrate must be perfectly dry; maximum relative humidity 12%; sand and dust.

Previously coated wood: if the primer coating is sound, sand and dust; otherwise, strip completely using REMOVER.

Standard plaster: allow to dry out, clean dirt stains.

Old walls: remove old paintwork, clean dirt stains.

Fill with MORGAN'S STUCCO IN PASTA or IN POLVERE.

Apply two coats of MURALITE 2000, leaving at least 12 hours and sanding between coats.

FINISH

After 24 hours, apply two coats of enamel, leaving at least 24 hours between coats.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of two or more coats of MURALITE to a thickness of 35 microns each on suitably prepared wooden substrates, sanding between coats.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 12		Thinner SYNTHETIC THINNER		Equipment cleaning SYNTHETIC THINNER		Roller application 5-10 % SYNTHETIC THINNER	
Appearance and finish MAT		Dust dry 1 HOUR		Specific weight kg/l 1.7		Brush application 5 % SYNTHETIC THINNER	
Colours WHITE		Touch dry after 2-3 HOURS		Solids by volume 55		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 12,000 cps.		Air assisted spraying 10-15% SYNTHETIC THINNER	
Shelf life 36 MONTHS		Overcoating interval 12 HOURS		Flash point =		=NOZZLE DIAM. 2 mm PRESSURE 2.5 atm	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230

