

**NEW LACK LUCIDO/SATINATO      B-01**  
**NEW LACK GLOSS/MAT**  
**Water-based acrylic enamel for exterior and interior use**



## PROPERTIES

Acrylic enamel featuring outstanding covering power, brushability and remarkable outdoor resistance. Available in both gloss and satin-finish versions.

GLOSS/SATIN-FINISH NEW LACK is particularly recommended for radiators.

## COATING SYSTEM

### SURFACE PREPARATION

**Iron:** remove any traces of rust and old flaking coats of enamel, sand down and dust.

Apply one or two coats of VERTOX and, after 24 hours, apply a coat of NEW FOND; allow to dry thoroughly for at least 8 hours.

**New wood:** fill any holes with MORGAN'S STUCCO IN PASTA; allow to dry, sand down and dust.

**Previously coated wood:** if old paintwork is in a poor state, strip and sand down; if it is in good condition, degrease and sand down.

Apply one or two coats of NEW FOND, allow to dry thoroughly for at least 8 hours, sand down and dust.

**Galvanized steel:** degrease thoroughly with a cloth soaked in thinner. Where necessary, remove zinc salts by brushing or blast cleaning. Apply a coat of NEW FOND, allow to dry thoroughly for at least 8 hours.

### FINISH

**Apply two coats of NEW LACK, leaving at least 8 hours between coats.**

## WARNINGS

Do not apply when humidity is high, with temperatures below +10°C or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, at a temperature over +5°C..

### TENDER SPECIFICATION ITEM

Application of NEW LACK, a blend of non-yellowing acrylic resin and resistant pigments, in two coats to a thickness of 25 microns each, on suitably prepared substrates.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 12		Thinner THINNER		Equipment cleaning SOAP AND WATER		Roller application 5-10 % WATER	
Appearance and finish GLOSS/SATIN-FINISH		Dust dry 2-3 HOURS		Specific weight kg/l 1.2-1.3		Brush application 5- 10 % WATER	
Colours WHITE, BLACK AND PROGRESS TONATONE		Touch dry after 5 HOURS		Solids by volume 38		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 95 K.U.		Air assisted spraying 10% WATER	
Shelf life 24 MONTHS		Overcoating interval 8 HOURS		Flash point =		=NOZZLE DIAM. - 2 mm PRESSURE -2.5 atm	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

**J COLORS S.p.A.**

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230

