

NEW WOOD IMPREGNANTE C-01
NEW WOOD PRESERVATIVE
Mat wood preservative



PROPERTIES

Clear and pigmented mat protective impregnating varnish for exterior and interior use. Instead of forming a film, it penetrates pores deep down, protecting wood from physical and biological attack.

COATING SYSTEM

SURFACE PREPARATION

New wood: wood must be seasoned and dry (maximum acceptable humidity 13%).

Sand with abrasive paper, clean and dust.

Resinous wood: clean away all traces of resin with a cloth soaked in synthetic thinner, sand with abrasive paper, clean and dust.

Previously coated wood: remove traces of old paintwork with REMOVER: apply paint remover with full brushstrokes to an even thickness, wait 5 -10 minutes then scrape old paintwork off with special scrapers, sand down to bare wood.

Clean surface with synthetic thinner and allow to dry thoroughly.

FINISH

Apply one or two coats of NEW WOOD IMPREGNANTE, leaving 6 hours between coats. If you want a gloss or waxed finish, apply one or two coats of NEW WOOD FLATTING or NEW WOOD FINITURA CERATA after 6 hours .

WARNINGS

Do not apply when humidity is high, with temperatures below +10°C or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, at a temperature over + 5 °C.

TENDER SPECIFICATION ITEM

Application of one or two coats of NEW WOOD IMPREGNANTE, a blend of acrylic copolymers and special additives formulated to protect wood from physical and biological attack.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 14		Thinner WATER		Equipment cleaning SOAP AND WATER		Roller application =	
Appearance and finish MAT		Dust dry 1 HOUR		Specific weight kg/l 1.03		Brush application 5-10% WATER	
Colours COLOUR CHART AND PROGRESS TONATONE		Touch dry after 2-3 HOURS		Solids by volume 20		Knife application =	
Exterior / interior use YES/YES		Through drying after 4 HOURS		Viscosity 68 K.U.		Air assisted spraying =	
Shelf life 24 MONTHS		Overcoating interval 6 HOURS		Flash point =			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230