

MORGAN'S WOOD COLOR IMPREGNANTE C-07
MORGAN'S WOOD COLOR PRESERVATIVE
Wood preservative



PROPERTIES

Clear and pigmented mat protective waterproofing impregnating varnish for exterior and interior use. Instead of forming a film, it penetrates pores deep down, protecting wood from physical and biological attack.

COATING SYSTEM

SURFACE PREPARATION

New wood: wood must be seasoned and dry (maximum acceptable humidity 13%).

Sand with abrasive paper, clean and dust.

Resinous wood: clean away all traces of resin with a cloth soaked in synthetic thinner, sand with abrasive paper, clean and dust.

Previously coated wood: remove traces of old paintwork with REMOVER: apply paint remover with full brushstrokes to an even thickness, wait 5 -10 minutes then scrape old paintwork off with special scrapers, sand down to bare wood.

Clean surface with synthetic thinner and allow to dry thoroughly.

FINISH

Apply the first coat of MORGAN'S WOOD COLOR IMPREGNANTE; after 20' – 30', rub down gently with a wool cloth.

After 24 hours, depending on the desired effect, apply two or more coats of MORGAN'S WOOD COLOR IMPREGNANTE or MORGAN'S WOOD COLOR IMPREGNANTE CERATO or MORGAN'S WOOD COLOR FLATTING or MORGAN'S WOOD COLOR FLATTING NAVALE 32, leaving 24 hours between coats.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of one or two coats of MORGAN'S WOOD COLOR IMPREGNANTE, a blend of glycerophthalic resins and special additives formulated to protect wood from physical and biological attack.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 15		Thinner SYNTHETIC THINNER		Equipment cleaning SYNTHETIC THINNER		Roller application =	
Appearance and finish MAT		Dust dry 2 HOURS		Specific weight kg/l 0.85		Brush application READY PRODUCT	
Colours COLOUR CHART AND PROGRESS TONATONE		Touch dry after 5 HOURS		Solids by volume 18		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 30'' FORD 4		Air assisted spraying =	
Shelf life 36 MONTHS		Overcoating interval 24 HOURS		Flash point 35°C			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230