

MORGAN'S WOOD VARNISH FLATTING NAVALE 32 C -17
MORGAN'S WOOD VARNISH NAVAL FLATTING 32
 Finishing wood varnish for exterior and interior use



PROPERTIES

Gloss clear finishing varnish for exterior use.

Protects and decorates wood, forming a flexible film providing great resistance and filling power which, rather than altering the colour of the substrate, brings out its natural grain.

COATING SYSTEM

SURFACE PREPARATION

New wood: wood must be seasoned and dry (maximum acceptable humidity 13%).

Sand with abrasive paper, clean and dust.

Resinous wood: clean away all traces of resin with a cloth soaked in synthetic thinner, sand with abrasive paper, clean and dust.

Previously coated wood: remove traces of old paintwork with REMOVER: apply paint remover with full brushstrokes to an even thickness, wait 5 -10 minutes then scrape old paintwork off with special scrapers, sand down to bare wood.

Clean surface with synthetic thinner and allow to dry thoroughly.

Apply a coat of MORGAN'S WOOD COLOR IMPREGNANTE.

FINISH

Apply two or three coats of MORGAN'S WOOD COLOR FLATTING NAVALE 32, leaving 24 hours between coats.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of one or two coats of MORGAN'S WOOD COLOR FLATTING NAVALE 32, a blend of glycerophthalic resins featuring remarkable elasticity.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 8		Thinner SYNTHETIC THINNER		Equipment cleaning SYNTHETIC THINNER		Roller application 5-10 % SYNTHETIC THINNER	
Appearance and finish GLOSS		Dust dry 1 HOUR		Specific weight kg/l 0.92		Brush application 5-10% SYNTHETIC THINNER	
Colours COLOURLESS		Touch dry after 4 HOURS		Solids by volume 37		Knife application =	
Exterior / interior use YES/YES		Through drying after 24 HOURS		Viscosity 180" FORD 4		Air assisted spraying 10-20% SYNTHETIC THINNER	
Shelf life 36 MONTHS		Overcoating interval 24 HOURS		Flash point 37°C		=NOZZLE DIAM. -1.7 mm PRESSURE -2 atm	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230