

ISOSOLV D-05

Solvent-based sealer for exterior use



PROPERTIES

Solvent-based vinylversatic resin-based masonry fixative sealer, ideal for old and new walls. Unsaponifiable, good throwing power and good consolidating power. Evens out absorption. Forms an ideal adhesive bridge between mineral substrates and finishes.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: allow to dry out, clean any dirt stains.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

Limewash or silicate paintwork: eliminate completely and dust.

Mouldy walls: after cleaning, restore with BIOSAN1. Allow to dry thoroughly.

Indoors, fill with MORGAN'S STUCCO IN PASTA or IN POLVERE and, outdoors, with special products.

Apply a coat of ISOSOLV thinned with 80% - 100% of nitro thinner depending on the kind of substrate.

After 24 hours, start applying the chosen finish.

WARNINGS

Do not apply when humidity is high, with low temperatures or on surfaces exposed to sunlight during application. Keep tin tightly sealed, upside down, in a cool place away from heat sources.

TENDER SPECIFICATION ITEM

Application of ISOSOLV fixative sealer formulated with a blend of special vinylversatic resins in solvent featuring remarkable throwing power. Apply with a brush or roller, thinned with nitro thinner in the ratio 1:1 by volume.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 12		Thinner NITRO		Equipment cleaning NITRO		Roller application 80-100 % NITRO	
Appearance and finish CLEAR		Dust dry =		Specific weight kg/l 0.88		Brush application 80-100 % NITRO	
Colours COLOURLESS		Touch dry after 4-6 HOURS		Solids by volume =		Knife application =	
Exterior / interior use YES/YES		Through drying after 12 HOURS		Viscosity 18''FORD 4		Air assisted spraying =	
Shelf life 36 MONTHS		Overcoating interval 24 HOURS		Flash point 25°			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230