

ACRYL WS 5000 F-04

Acrylic washable paint for exterior and interior use



PROPERTIES

Water-based washable acrylic emulsion paint for exterior and interior use featuring exceptional covering power, outstanding spreading rate. Easy to apply, mat velvet finish.
Wet abrasion resistance 5,000 cycles, UNICHIM method.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: allow to dry out, clean any dirt stains.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

Limewash or silicate paintwork: eliminate completely and dust.

Mouldy walls: after cleaning, apply BIOSAN 1. Allow to dry thoroughly.

Indoors, fill with MORGAN'S STUCCO IN PASTA or IN POLVERE and, outdoors, with special products.

Apply a coat of sealer, taking care to choose the one most suitable for the kind of substrate, MORGAN'S FLEX, WUNDER FLEX, FISSATIVO, ISOSOLV, PONTE DI ANCORAGGIO. For premixed surfaces, apply a coat of odourless solvent-based sealer PONTE DI ANCORAGGIO only.

FINISH

Allow to dry thoroughly. Apply two coats of ACRYL WS 5000, leaving approx. 4 - 5 hours between coats.

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5 °C. Do not apply on surfaces that are warm or exposed to sunlight. Keep out of the rain for at least two or three days. Keep in tightly sealed tin, at a temperature over +5°C.

TENDER SPECIFICATION ITEM

Brush, roller or spray application of ACRYL WS 5000, washable emulsion paint for exterior and interior use formulated with a blend of water-based acrylic resin and select light-fast pigments.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

| | | | | | | | |
|---|--|----------------------|--|----------------------|--|--|--|
| Theoretical spreading rate Per coat sq m/l | | Thinner | | Equipment cleaning | | Roller application | |
| 12 | | WATER | | WATER | | 30-40 % WATER | |
| Appearance and finish | | Dust dry | | Specific weight kg/l | | Brush application | |
| MAT | | = | | 1.5 | | 30-40% WATER | |
| Colours | | Touch dry after | | Solids by volume | | Knife application | |
| WHITE AND PROGRESS TONATONE | | 30' | | 45 | | = | |
| Exterior / interior use | | Through drying after | | Viscosity | | Air assisted spraying | |
| YES/YES | | 24 HOURS | | 112 K.U. | | 30-40 % WATER | |
| Shelf life | | Overcoating interval | | Flash point | | NOZZLE DIAM. -1.5 mm PRESSURE -2.5-3 atm AIRLESS NOZZLE DIAM. -0.66 mm PRESSURE -100-200 atm | |
| 24 MONTHS | | 4-5 HOURS | | = | | | |

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230