

CITY F-09

Velvet-finish washable emulsion paint for exterior and interior use



PROPERTIES

Breathable washable emulsion paint for interior use. Easy to apply, outstanding covering power and mat velvety appearance. High vapour permeability.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: allow to dry out, clean any dirt stains.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

Limewash or silicate paintwork: eliminate completely and dust.

Mouldy walls: after cleaning, restore with BIOSAN 1. Allow to dry thoroughly.

Fill with MORGAN'S STUCCO IN PASTA or IN POLVERE.

Apply a coat of sealer, taking care to choose the one most suitable for the kind of substrate, MORGAN'S FLEX, WUNDER FLEX, FISSATIVO, PONTE DI ANCORAGGIO. For premixed surfaces, apply a coat of odourless solvent-based sealer PONTE DI ANCORAGGIO only.

FINISH

Allow to dry thoroughly. Apply two coats of CITY, leaving approx. 4 -5 hours between coats.

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5°C. Keep in tightly sealed tin, at a temperature over +5°C.

TENDER SPECIFICATION ITEM

Brush, roller or spray application of CITY, breathable washable emulsion paint for interior use, formulated with a blend of acrylic styrene resin, titanium-dioxide and calcium carbonate.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l		Thinner		Equipment cleaning		Roller application	
8		WATER		WATER		30-40 % WATER	
Appearance and finish		Dust dry		Specific weight kg/l		Brush application	
MAT		=		1.6		30-40% WATER	
Colours		Touch dry after		Solids by volume		Knife application	
WHITE AND PROGRESS TONATONE		3-4 HOURS		46		=	
Exterior / interior use		Through drying after		Viscosity		Air assisted spraying	
NO/YES		12 HOURS		35000 cps.		40 % WATER	
Shelf life		Overcoating interval		Flash point		NOZZLE DIAM. 1.5 -1.7 mm PRESSURE 2.5 -3 atm AIRLESS NOZZLE DIAM. 0.66 mm PRESSURE 100 -200 atm	
24 MONTHS		4-5 HOURS		=			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230