

PLAYTON F-15

Masonry paint for interior use



PROPERTIES

Masonry paint for interior use. Outstanding transpiration, good covering power and white point. Easy to apply, velvet finish.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: allow to dry out, clean any dirt stains.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

Limewash or silicate paintwork: eliminate completely and dust.

Mouldy walls: after cleaning, restore with BIOSAN 1. Allow to dry thoroughly.

Fill with MORGAN'S STUCCO IN PASTA or IN POLVERE.

Apply a coat of sealer: taking care to choose the one most suitable for the kind of substrate, MORGAN'S FLEX, WUNDER FLEX, FISSATIVO, PONTE DI ANCORAGGIO. For premixed surfaces, apply a coat of odourless solvent-based sealer PONTE DI ANCORAGGIO only.

FINISH

Allow to dry thoroughly. Apply two coats of PLAYTON, leaving approx. 4 -5 hours between coats.

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5 °C. Keep in tightly sealed tin, at a temperature over +5°C.

TENDER SPECIFICATION ITEM

Brush, roller or spray application of PLAYTON, paint for interior use formulated with a blend of vinylversatic resin, titanium-dioxide and calcium carbonate.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l		Thinner		Equipment cleaning		Roller application	
6		WATER		WATER		30-40 % WATER	
Appearance and finish		Dust dry		Specific weight kg/l		Brush application	
MAT		=		1.6		40-50% WATER	
Colours		Touch dry after		Solids by volume		Knife application	
WHITE		2 HOURS		=		=	
Exterior / interior use		Through drying after		Viscosity		Air assisted spraying	
NO/YES		12 HOURS		40000 cps.		40 % WATER	
Shelf life		Overcoating interval		Flash point		NOZZLE DIAM. 1.5 -1.7 mm PRESSURE 2.5 -3 atm AIRLESS NOZZLE DIAM. 0.66 mm PRESSURE 100 -200 atm	
24 MONTHS		4-5 HOURS		=			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230