

MORGAN'S SILICON G-11

Odourless solvent-based silicone protective covering



PROPERTIES

Odourless solvent-solution silicone protective covering for exterior use. Does not block substrate pores, enabling it to breathe. Impervious to weathering. Can be used on substrates with low or high absorption, on light and dark plaster, on exposed brickwork or stone of a sedimentary nature.

COATING SYSTEM

Standard plaster: allow to dry out, clean any dirt stains.

Exposed brickwork or stone: clean dirt stains and any incrustations of cement or concrete.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, strip completely and wash with water.

Limewash or silicate paintwork: eliminate completely and dust.

Mouldy walls: brush and clean, disinfect with relevant products.

FINISH

Continue applying coats of MORGAN'S SILICON, leaving two hours between coats, until the substrate can absorb no more.

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5°C. Do not apply on surfaces that are warm or exposed to sunlight. Keep in tightly sealed tin, at a temperature over +5°C.

Product cannot be coated over with other paints.

TENDER SPECIFICATION ITEM

Application of two or more coats of MORGAN'S SILICON solvent-based silicone impregnating agent on suitably prepared substrates.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l		Thinner		Equipment cleaning		Roller application	
16		TURPENTINE		TURPENTINE		READY PRODUCT	
Appearance and finish		Dust dry		Specific weight kg/l		Brush application	
CLEAR		5'		0.8		READY PRODUCT	
Colours		Touch dry after		Solids by volume		Knife application	
COLOURLESS		1 HOUR		=		=	
Exterior / interior use		Through drying after		Viscosity		Air assisted spraying	
YES/YES		24 HOURS		14'' FORD 8		READY PRODUCT	
Shelf life		Overcoating interval		Flash point		NOZZLE DIAM.: 1.5 – 1.7 mm PRESSURE: 2 atm.	
36 MONTHS		2 HOURS		39°C			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230