

MORGAN'S PLASTIC LAVABILE AL QUARZO FINE H-05
MORGAN'S PLASTIC WASHABLE FINE QUARTZ PAINT
Fine-quartz wall covering for exterior and interior use



PROPERTIES

Fine-particle quartz paint for interior and exterior use formulated with a blend of water-based acrylic styrene resin, select pigments and quartz flour.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: allow to dry out, clean any dirt stains.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

Lime wash or silicate paintwork: eliminate completely and dust.

Mouldy walls: after cleaning, restore with BIOSAN 1. Allow to dry thoroughly.

Indoors, fill with MORGAN'S STUCCO IN PASTA or IN POLVERE and, outdoors, with special products.

Apply a coat of sealer, taking care to choose the one most suitable for the kind of substrate, MORGAN'S FLEX, WUNDER FLEX, FISSATIVO, ISOSOLV, PONTE DI ANCORAGGIO. For premixed surfaces, apply a coat of odourless solvent-based sealer PONTE DI ANCORAGGIO only.

FINISH

Allow to dry thoroughly. Apply two coats of MORGAN'S PLASTIC LAVABILE AL QUARZO FINE, leaving approx. 6 -8 hours between coats.

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5 °C. Do not apply on surfaces that are warm or exposed to sunlight. Keep out of the rain for at least two or three days. Keep in tightly sealed tin, at a temperature over +5 °C.

TENDER SPECIFICATION ITEM

Application of fine-particle wall covering MORGAN'S PLASTIC LAVABILE AL QUARZO FINE, a blend of acrylic styrene polymers, select pigments and quartz flour, on suitably prepared substrates.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l		Thinner		Equipment cleaning		Roller application	
10		WATER		WATER		15-20 % WATER	
Appearance and finish		Dust dry		Specific weight kg/l		Brush application	
MAT		=		1.65		20-30 % WATER	
Colours		Touch dry after		Solids by volume		Knife application	
WHITE AND PROGRESS TONATONE		3-4 HOURS		=		=	
Exterior / interior use		Through drying after		Viscosity		Air assisted spraying	
YES/YES		24 HOURS		35000 cps.		30% WATER	
Shelf life		Overcoating interval		Flash point		NOZZLE DIAM. 1.7 -1.9 mm PRESSURE 3 -4 atm	
24 MONTHS		6- 8 HOURS		=			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230