

MORGAN'S PLASTIC LUCIDO H-11
MORGAN'S PLASTIC GLOSS
Textured paint for gloss finishes for interior use



PROPERTIES

Textured paint for gloss finishes for interior use, formulated with a blend of water-based copolymers. Gives the substrate a gloss finish and excellent resistance to washing with household detergents.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: allow to dry out, clean any dirt stains.

Water-based paintwork and varnishes: if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

Limewash or silicate paintwork: eliminate completely and dust.

Mouldy walls: after cleaning, restore with BIOSAN 1. Allow to dry thoroughly.

Fill with MORGAN'S STUCCO IN PASTA or IN POLVERE.

Apply a coat of sealer, taking care to choose the one most suitable for the kind of substrate, MORGAN'S FLEX, WUNDER FLEX, FISSATIVO, PONTE DI ANCORAGGIO . For premixed surfaces, apply a coat of odourless solvent-based sealer PONTE DI ANCORAGGIO only.

FINISH

Brush on a coat of MORGAN'S PLASTIC LUCIDO thinned with water at 20 -30 % and, after 12 hours, apply a second coat of the product with a roller without thinning, or thinned at 5% depending on the kind of texture desired.

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5 °C. Keep in tightly sealed tin, at a temperature over +5°C.

TENDER SPECIFICATION ITEM

Application of gloss-finish washable textured paint MORGAN'S PLASTIC LUCIDO for interior use, a blend of internal-plasticization water-based copolymers and select pigments, on suitably prepared substrates.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 2		Thinner WATER		Equipment cleaning WATER		Roller application 0-5% WATER	
Appearance and finish GLOSS		Dust dry =		Specific weight kg/l 1.17		Brush application 20-30 % WATER	
Colours WHITE AND PROGRESS TONATONE		Touch dry after 4-6 HOURS		Solids by volume 38		Knife application =	
Exterior / interior use NO/YES		Through drying after 48 HOURS		Viscosity 138 K.U.		Air assisted spraying =	
Shelf life 24 MONTHS		Overcoating interval 12-24 HOURS		Flash point =			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230