

MORGAN'S PRIMER ACRILICO D2 H-13

MORGAN'S ACRYLIC PRIMER D2



PROPERTIES

Water-based acrylic fixative with a blend of ultrafine acrylic particles dispersed in the vehicle, formulated specially for the no-crack elastomeric system. This fixative features exceptional throwing power on all kinds of substrates and is perfectly compatible with other products belonging to the same coating system, ensuring they adhere perfectly to the surface.

COATING SYSTEM

SURFACE PREPARATION

Standard plaster: after drying out, clean any dirt stains.

Substrates with old synthetic resin-based coats. if sound, dry clean or wash; otherwise, eliminate old paintwork and wash with water.

Lime- or silicate-based primers: eliminate completely and wash with water.

Prepared substrates must be treated with one or more coats of MORGAN'S PRIMER ACRILICO D2, brushed on thinned with water in the ratio 1:1. On particularly inconsistent substrates, it is advisable to apply an additional preventive coat thinned in the ratio 1:2 or 1:3.

FINISH

Apply two coats of MORGAN'S PRIMER ACRILICO D2, leaving 12 hours between coats.

COLOUR Beige

WARNINGS

Do not apply when temperature of the air, substrate or product is below +5 °C.

In addition, do not apply on warm surfaces exposed to sunlight. Keep in tightly sealed tin, at a temperature in the range +5 °C/+35 °C.

MAIN DATA AT 20°C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 10-13		Thinner WATER		Equipment cleaning WATER		Roller application NOT RECOMMENDED	
Appearance and finish =		Dust dry =		Specific weight kg/l 1.2		Brush application WATER 1:1	
Colours BEIGE		Touch dry after 5 HOURS		Solids by volume 21.6		Knife application =	
Exterior / interior use YES/YES		Through drying after 12 HOURS		Viscosity 3000 cps.		Air assisted spraying NOT RECOMMENDED	
Shelf life 24 MONTHS		Overcoating interval 12 HOURS		Flash point =			

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

J COLORS S.p.A.

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230