

# COLORART DALI' I-05

## Polychromatic water-based paint



### PROPERTIES

Water-based multicolour decorative wall covering, formulated with a blend of styrene-acrylic copolymers. Odourless, remarkable elasticity, exceptionable washability.

Available in three tinting bases: WHITE, LIGHT, DARK for PROGRESS TONATONE colour matching system.

### COATING SYSTEM

#### SURFACE PREPARATION

**Standard plaster:** allow to dry out, clean any dirt stains.

**Water-based paintwork and varnishes:** if sound, dry clean or wash; otherwise, eliminate completely and wash with water.

**Mouldy walls:** after cleaning, restore with BIOSAN 1. Allow to dry thoroughly.

Fill with MORGAN'S STUCCO IN PASTA or IN POLVERE.

Apply a coat of FISSATIVO fixative. For premixed surfaces, apply a coat of odourless solvent-based sealer PONTE DI ANCORAGGIO only.

**APPLY ONE OR TWO COATS:** apply one or two coats of MORGAN'S PLASTIC LAVABILE AL QUARZO FINE or QUARZO EXTRA-FINE, leaving 6 - 8 hours between coats.

#### FINISH

Thin COLORART DALI' with water at 15 – 20%.

Spray application entails masking any parts not to be coated.

Spray COLORART DALI' on using an air compressor. Apply two coats in a crisscross pattern, wet on wet, at a distance of approx. 50 cm from the surface, keeping the gun at a right angle to the surface.

**PROTECTIVE FINISH:** for unbeatable protection, apply a coat of satin-finish acrylic protective varnish DECORLAC with UV filters.

### WARNINGS

Do not apply when temperature of the air, substrate or product is below +5 °C.

Do not mix the product with a mixer or mechanical equipment: stir by hand with a knife.

Keep to the spreading rates given on the sheet or work cannot be touched up or resumed, and the colour will not be the same as the colour chart.

MAIN DATA AT 20 °C AND 70 % RELATIVE HUMIDITY

Theoretical spreading rate Per coat sq m/l 2.5		Thinner WATER		Equipment cleaning WATER		Roller application =	
Appearance and finish MAT MULTICOLOURED		Dust dry =		Specific weight kg/l 1		Brush application =	
Colours WHITE, LIGHT, DARK AND PROGRESS TONATONE		Touch dry after 4-8 HOURS		Solids by volume =		Knife application =	
Exterior / interior use NO/YES		Through drying after 24 HOURS		Viscosity 7000 cps.		Air assisted spraying 15-20% WATER	
Shelf life 12 MONTHS		Overcoating interval 12 HOURS		Flash point =		NOZZLE DIAM. -2.5 mm PRESSURE -2 -2.5 atm	

As conditions and feasibility of use may be influenced by external factors beyond the manufacturer's control, the Company declines all responsibility for results.

**J COLORS S.p.A.**

Via Settembrini, 39 - 20020 Lainate (MI) - Italy - Tel. ++ 39 02 937541 - Fax ++ 39 02 9374114

EDITION 6/ 99 1230